

MAY 27TH, 2008

TELEFAX TO : TO WHOM IT MAY CONCERN
TELEFAX FROM : PATRICK TAKKENBERG
NUMBER OF PAGES : 2 (INCLUDING THIS PAGE)

PLEASE TAKE NOTE OF THE FOLLOWING ANALYTICAL RESULTS

OUR REF. : 81232
MATERIAL : APR
PACKING : 8 bags in 1 drum
ADV. GROSS WEIGHT : 75.741 KGS
ADV. NET WET WEIGHT : 72.180 KGS
MOISTURE : 0,042 %
NET DRY WEIGHT : 72.150 KGS
SAMPLING DATE : 21-04-2008

Rhenium	(Re) =	69,3	%
Boron	(B) =	< 0,0001	%
Carbon	(C) =	< 0,005	%
Nitrogen	(N) =	5,10	%
Oxygen	(O) =	23,90	%
Sodium	(Na) =	< 0,0002	%
Magnesium	(Mg) =	< 0,0001	%
Aluminium	(Al) =	0,0001	%
Silicon	(Si) =	< 0,0002	%
Phosphorus	(P) =	< 0,0001	%
Sulphur	(S) =	0,0013	%
Potassium	(K) =	< 0,001	%
Calcium	(Ca) =	< 0,0003	%
Titanium	(Ti) =	< 0,0001	%
Vanadium	(V) =	< 0,0001	%
Chromium	(Cr) =	< 0,0001	%
Manganese	(Mn) =	< 0,0001	%
Iron	(Fe) =	< 0,0001	%
Cobalt	(Co) =	< 0,0001	%
Nickel	(Ni) =	< 0,0001	%
Copper	(Cu) =	< 0,0001	%
Zinc	(Zn) =	< 0,0001	%
Gallium	(Ga) =	< 0,0001	%

ANALYSES RELATES TO THE MATERIAL IN THE ORIGINAL STATE.

SEALED: - ASA -

THANKS AND BEST REGARDS

Alex Stewart B.V.

Geysendorfferweg 58
3088 GK Rotterdam, The Netherlands
P.O. Box 53062
3008 HB Rotterdam, The Netherlands
Tel +31 10 4287888
Fax +31 10 4287865
www.alexstewart.com



**Alex
Stewart**
INSPECTION & ANALYSIS

OUR REF. :81232

Page 2 of 2

Arsenic	(As) =	< 0,0001 %
Selenium	(Se) =	< 0,0005 %
Zirconium	(Zr) =	< 0,0001 %
Niobium	(Nb) =	< 0,0001 %
Molybdenum	(Mo) =	0,0016 %
Silver	(Ag) =	< 0,0001 %
Cadmium	(Cd) =	< 0,0001 %
Indium	(In) =	< 0,0001 %
Tin	(Sn) =	< 0,0001 %
Antimony	(Sb) =	< 0,0001 %
Tellurium	(Te) =	< 0,0001 %
Barium	(Ba) =	< 0,0001 %
Hafnium	(Hf) =	< 0,0001 %
Tantalum	(Ta) =	< 0,001 %
Tungsten	(W) =	< 0,0001 %
Thallium	(Tl) =	< 0,0001 %
Lead	(Pb) =	< 0,0001 %
Bismuth	(Bi) =	< 0,0001 %
Thorium	(Th) =	< 0,0001 %

**ANALYSES RELATES TO THE MATERIAL IN THE ORIGINAL STATE.
SEALED: - ASA -
THANKS AND BEST REGARDS**